PROPRIETARY PORTLAND CEMENT CONCRETE SEALERS

SM Material Code: 909M00050

Specification Reference: 909.10

Concrete surfaces shall be 28 days or older prior to application. If rain occurs, surface shall be allowed to dry at least 48 hours prior to sealing. Sealer shall be applied at the rate of 90 to 100 sft/gal (2.2 to $2.5~\text{m}^2/\text{l}$). Spray applications shall be accomplished using a low pressure, approximately 15 psi (103 kPa), non-atomizing spray equipment adjusted to the wet spray condition. Sealer shall be applied to vertical surfaces so that spray pattern will run 6 to 8 inches (150 to 200 mm) before soaking in. Horizontal surfaces shall be completely flooded. Sealer shall not be applied when wind conditions may cause overspray.

Mat. Source Manufacturer Approval Code Code Product Name Number

Shall not be applied if surface, ambient, or sealer temperature is below 40 $^{\circ}F$ (4.5 $^{\circ}C$) or above 100 $^{\circ}F$ (38 $^{\circ}C$). Sealer shall be applied with spray equipment.

9551 9554 BASF CONSTRUCTION CHEMICALS, LLC - BUILDING SYSTEMS -------W028330 ENVIROSEAL 40 (INDOT CLEAR SEALER)

Shall not be applied if surface, ambient, or sealer temperature is below 40 $^{\circ}F$ (4.5 $^{\circ}C$) or above 100 $^{\circ}F$ (38 $^{\circ}C$). Sealer shall be applied with spray equipment.

Shall not be applied if surface temperature is below 20 $^{\circ}F$ (-7 $^{\circ}C$) or above 100 $^{\circ}F$ (38 $^{\circ}C$). Sealer shall be applied with spray equipment.

Shall not be applied if surface or ambient temperature is below 32 $^{\circ}F$ (0 $^{\circ}C$) or above 100 $^{\circ}F$ (38 $^{\circ}C$). Sealer shall be applied with brush, roller, or spray equipment. Airless spray equipment preferred.

Shall not be applied if surface or ambient temperature is below 32 $^{\circ}F$ (0 $^{\circ}C$) or above 100 $^{\circ}F$ (38 $^{\circ}C$). Sealer shall be applied with brush, roller, or spray equipment. Airless spray equipment preferred.

Shall not be applied if surface or ambient temperature is below 32 $^{\circ}F$ (0 $^{\circ}C$) or above 100 $^{\circ}F$ (38 $^{\circ}C$). Sealer shall be applied with brush, roller, or spray equipment. Airless spray equipment preferred.